

B ROURKE "VINYLAST"

PRODUCT DATA SHEET

INTENDED USE

A rapid drying, non-convertible coating for application to ferrous and non-ferrous, decorative and structural metalwork where a high level of corrosion resistance is required. It may also be used as a one-coat primer/finish directly to most adequately prepared metals, and in particular exhibits good adhesion to well - prepared galvanised steel (see Suitable Substrates and Preparation).

CHARACTERISTICS

- ▶ Quick drying by solvent evaporation gives tack free time of 20 minutes.
- ▶ Ideally suited to conventional and airless spray application
- ▶ Non-sag properties allow good film build to 125 microns d.f.t..
- ▶ For exterior exposure, apply a minimum dry film thickness of 75 microns, but for marine and coastal environments apply 125 microns.
- ▶ Can be applied down to 5°C.
- ▶ Tough, flexible film, resistant to many aqueous chemicals.
- ▶ Excellent adhesion to hot dip galvanised ironwork, and aluminium.
- ▶ Reduces maintenance costs compared with conventional paint – re-painting intervals can be doubled, and only one coat is needed for re-painting.
- ▶ Full BS, RAL and NCS colour range available.

SUITABLE SUBSTRATES AND PREPARATION

Surfaces must be dry, sound and free from dirt, dust, rust and grease. Steel surfaces should be preferably blast cleaned to ISO 8501 part A1 Sa 2½ or wire brushed to BS7079 Part A1 ST2. Galvanised steel should be free of White rust (zinc corrosion deposits) and if previously weathered should be washed with copious quantities of water to remove soluble salts. Galvanised steel that has been oiled should be thoroughly cleaned to remove all traces of oil prior to coating. Heavily chromated galvanised steel should be alkali cleaned to remove the chromate passivation. Bright spangled galvanised steel will require pre-treatment with Rourke's Wash Primer, a Mordant solution or abrading thoroughly using P600 wet or dry abrasive paper before application of Vinylast.

AVAILABILITY

A low satin finish, available in standard colours from stock in 1ltr, 2.5ltr, 5ltr and 20ltr containers. Most BS, RAL and NCS colours in 1litre to 20 litre containers are available to order.

PRODUCT INFORMATION (TYPICAL FIGURES)

Composition	Based on a modified vinyl resin, pigmented with suitably selected pigments, and zinc phosphate anticorrosive pigment.
Volume Solids	37% for matt black
VOC content	585 gm/litre.
Supply viscosity	5 poise at 20°C
Typical film thickness	200 microns wet and 75 microns dry.
Coverage	Theoretical coverage is 4.5 sq. metres/litre at 200 microns wet film thickness. The spreading rate of this product will vary considerably depending on the method of application and the roughness and porosity of the surface. In practice, this figure may be reduced by up to 40%.
Dry heat resistance	60°C
Specific Gravity	1.2
Flash Point	Within the range 21 – 31°C

APPLICATION DETAILS

PREFERABLY BRING PAINT TO 15-20°C. STIR WELL BEFORE USE.

Airless spray (cold) Up to 5% thinners may be added to suit equipment.
Typical tip size 13-19 thou.
Typical fluid pressure 200 kg/sq. metre or 2800 p.s.i.

Conventional spray Up to 15 % Thinners may be added to suit equipment but a lower film thickness will be achieved.

Brush/Roller Apply evenly using a well-loaded brush. Do not attempt to brush out or lay off.

Thinner Fast Flash Thinner is recommended for spraying and cleaning.

Film thickness per coat

	Dry	Wet
Minimum	25 microns	80 microns
Maximum	75 microns	240 microns

DRYING AND RECOATING

Approximate drying times at 40 microns d.f.t.

Substrate temperature	Touch dry	Dry to handle	Overcoating times	
			Minimum	Maximum
10°C	45 mins	2 hours	2 hours	Indefinite
20°C	20 mins	1 hour	1 hour	

Environmental Conditions The air temperature should be at least 5°C with a surface temperature 3°C above dew point and the relative humidity below 90%, thus ensuring that the surface is dry and that condensation will not occur during application or drying. The drying times will be significantly extended in cold, damp conditions.

Overcoating/Repainting For inland exterior environments a minimum dry film thickness of 75 microns must be achieved.
For coastal/marine environments a minimum of 125 microns is recommended.

SHELF LIFE

After a period of storage the product should be thoroughly stirred. Usable life 1 year from date of manufacture in unopened containers, protected from heat.

SAFETY PRECAUTIONS

REFER TO THE MATERIAL SAFETY DATA SHEET

Reference No. VINYLAST

SPVYHB-4 ISSUED 02/2005

THIS DATA SHEET SUPERCEDES ALL PREVIOUS ISSUES. The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, since the conditions of use are beyond our control. This data sheet does not constitute a specification.

In case of doubt as to the suitability of the product, please contact our Technical Service Department. Please use in conjunction with your clients specifications.

SUPPLEMENTARY PRODUCT INFORMATION

REPAIRS RECTIFICATION AND MAINTENANCE OF THE COATING

Vynylast coatings are very easy to repair and maintain. The risk of Intercoat adhesion is minimal compared to a two pack or alkyd coatings. The process should be;

1. Thoroughly clean the surface and lightly abrade
2. If any areas of bare metal are showing, remove all trace of corrosion and spot prime with two generous coats of Vynylast to a minimum of 50 microns d.f.t
3. Allow to dry overnight and flat back the edges of the repair to give a smooth finish.
4. Apply one coat to a minimum of 25 microns d.f.t. to the entire painted area (or further coats if specified)

CAN I USE A PRIMER?

Vynylast is a self priming topcoat for all typical uses and exhibits a level of adhesion and durability far superior to conventional alkyd primers

DO NOT USE PRIMERS UNDER VINYLAST unless specifically advised by our Technical Department. Examples may be:

1. **Non ferrous metals**.....Rourke's Wash Primer
2. **For extreme corrosion resistance**.....Rourke's 2 Pack Epoxy Zinc Phosphate Prime on ferrous metals

APPLICATION TIPS BY BRUSH/ROLLER generously

Application Because the product is fast drying the solvent evaporates very quickly and there is no wet-edge, so lay the paint on and leave it to "flow out"

Typical film thickness

One generous coat achieves a maximum w.f.t. of 75 microns equal to 25 microns d.f.t

Recoating Because the product is "non convertible" (i.e. re-dissolves in its own solvent) it will "pick up under the brush" when a second coat is applied. Leave for 24 hours between coats to minimise the effect.

APPLICATION TIPS WHEN SPRAYING

Electrostatic Ready for use with most equipment. Gives excellent wrap under most circumstances. If required use Rourke's Industrial Thinners.

Airless Spray Gives excellent sag resistance enabling 250 microns w.f.t.(75 microns d.f.t) be applied in one application.

END USE RESTRICTIONS

DO NOT apply to handrails...a 2 pack system is recommended

DO NOT apply to surfaces exposed to oil, petrol, splashes etc. The dry film readily dissolves.

DO NOT apply to surfaces subjected to temperatures above 60 °C

DO NOT apply to fabrications where early hardness development/resistance to pressure marking is required. The coating remains flexible and softer than conventional paint for 7-14 days dependent on film thickness. Not suitable for end uses, which require heavy goods to be placed or stacked upon it,

or, where early transportation of heavy items is required.

DO NOT apply to newly galvanised surfaces. These surfaces have micro air pockets within the zinc coating and should be left for 3-5 days to stabilise, prior to painting.

ALWAYS Apply sufficient film thickness to protect the surface being painted.

IS IT AVAILABLE IN A GLOSS FINISH

Rourke's Vinygloss is based on the same advanced resin technology and may be applied as a glossy top coat using Rourke's Vinylast as a primer undercoat

SPECIAL END USES

Chemical resistance – Good, resists most dilute acids, alkalis and chemicals.

Low temperature use - Dries well at low temperatures down to 0°C. When dry can be used on fabrications down to -20°C and more. Seek technical advice.

Tough Coatings - Resistant to knocks and impacts which would lead to flexible chipping and flaking of alkyd type coatings

Special black lead effect - with the MIO Graphite Grey version

SALES OPPORTUNITIES

directly
mild steel

Sign Industry - One coat reduced sheen finish, which adheres Foamex, abraded aluminium, galvanised and

Street Furniture - Adheres to a wide variety of substances, cast aluminium, zinc coated steel, mild steel etc.

Externally coated Plastic cladding - New factory units etc.

Reference No. VINYLAST

SPVYHB-4 ISSUED 02/2005

THIS DATA SHEET SUPERCEDES ALL PREVIOUS ISSUES The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, since the conditions of use are beyond our control. This data sheet does not constitute a specification.

In case of doubt as to the suitability of the product, please contact our Technical Service Department. Please use in conjunction with your clients specifications.

SAFETY DATA SHEET

VINYLAST
(General colours)

Version 5.03 2005,24 March
VY/GENERAL

Page 01

1. PRODUCT AND COMPANY IDENTIFICATION

1.01 Product Code VY/GENERAL
 1.02 Product Name HI-BUILD VINYLAST
 1.03 Synonyms
 (General colours)
 1.04 Intended Use A solvent borne paint for industrial finishing.
 Application may be by spray or special processes.
 1.05 Manufacturer/Supplier B Rourke & Co Ltd
 1.06 Address Accrington Road
 Burnley
 Lancashire
 BB11 5QD
 1.07 Contact Health & Safety Dept
 1.08 Phone Number 01282-422841
 1.09 Fax Number 01282-430240
 1.10 Emergency Phone Number 01282-422841

2. COMPOSITION/INFORMATION ON INGREDIENTS

2.01 General Information The hydrocarbon solvents used in this product contain less than 0.1% (w/w) of BENZENE.

2.02 Substances presenting a health or environmental hazard within the meaning of the CHIP Regulations or which are assigned occupational Exposure Limit Values.

Name	% Conc.	EC No.	Symbol	R-Phrases
(CAS 001330-20-7) XYLENE	25 - 50	215-535-7	Xn	R10 R20/21 R38
(CAS 007779-90-0) TRIZINC BIS(ORTHOPHOSPHATE)	2.5 - 10	231-944-3	N	R50/53
(CAS 000123-86-4) n-BUTYL ACETATE	2.5 - 10	204-658-1		R10 R66 R67
(CAS 064742-95-6) SOLVENT NAPHTHA (PETROLEUM), LIGHT AROMATICS	2.5 - 10	265-199-0	Xn N	R10 R51/53 R66 R67
(CAS 000100-41-4) ETHYLBENZENE	2.5 - 10	202-849-4	F Xn	R11 R20
(CAS 000108-65-6) 2-METHOXY-1-METHYLETHYL ACETATE	2.5 - 10	203-603-9	Xi	R10 R36
(CAS 000095-63-6) 1,2,4-TRIMETHYLBENZENE	2.5 - 10	202-436-9	Xn N	R10 R20 R36/37/38 R51/53
(CAS 000108-67-8) MESITYLENE	0.5 - 1.0	203-604-4	Xi N	R10 R37 R51/53
(CAS 000098-82-8) CUMENE	0.5 - 1.0	202-704-5	Xi N	R10 R37 R51/53
(CAS 068308-64-5) QUATERNARY AMMONIUM ETHOSULPHATE	0.1 - 0.5	269-662-8	C N	R34 R22 R50

2.03 R-Phrases used

SAFETY DATA SHEET

VINYLAST
(General colours)

Version 5.03 2005,24 March
VY/GENERAL

Page 02

2. COMPOSITION/INFORMATION ON INGREDIENTS (continued)

R10	FLAMMABLE.
R11	HIGHLY FLAMMABLE.
R20	HARMFUL BY INHALATION.
R20/21	HARMFUL BY INHALATION AND IN CONTACT WITH SKIN.
R22	HARMFUL IF SWALLOWED.
R34	CAUSES BURNS.
R36	IRRITATING TO EYES.
R36/37/38	IRRITATING TO EYES, RESPIRATORY SYSTEM AND SKIN.
R37	IRRITATING TO RESPIRATORY SYSTEM.
R38	IRRITATING TO SKIN.
R50	VERY TOXIC TO AQUATIC ORGANISMS.
R50/53	VERY TOXIC TO AQUATIC ORGANISMS, MAY CAUSE LONG-TERM ADVERSE EFFECTS IN THE AQUATIC ENVIRONMENT.
R51/53	TOXIC TO AQUATIC ORGANISMS; MAY CAUSE LONG-TERM ADVERSE EFFECTS IN THE AQUATIC ENVIRONMENT.
R65	HARMFUL: MAY CAUSE LUNG DAMAGE IF SWALLOWED.
R66	REPEATED EXPOSURE MAY CAUSE SKIN DRYNESS OR CRACKING.
R67	VAPOURS MAY CAUSE DROWSINESS AND DIZZINESS.

3. HAZARD IDENTIFICATION

3.01 Main Hazards	The product has been assigned the following indications of danger: FLAMMABLE & HARMFUL
3.02 Health Effects - Skin	HARMFUL AND IRRITATING TO THE SKIN.
3.03 Health Effects - Inhalation	HARMFUL BY INHALATION.
3.04 General Information	HARMFUL TO AQUATIC ORGANISMS, MAY CAUSE LONG-TERM ADVERSE EFFECTS IN THE AQUATIC ENVIRONMENT.

4. FIRST AID MEASURES

4.01 General	In all cases of doubt, or when symptoms persist, seek medical attention. Never give anything by mouth to an unconscious person.
4.02 First Aid - Eyes	Remove contact lenses. Irrigate copiously with clean, fresh water for at least 10 minutes holding the eyelids apart, and seek medical advice.
4.03 First Aid - Skin	Remove contaminated clothing. Wash skin thoroughly with soap and water or use proprietary skin cleaner. Do NOT use solvents or thinners.
4.04 First Aid - Ingestion	If accidentally swallowed obtain immediate medical attention. Keep at rest. Do NOT induce vomiting.
4.05 First Aid - Inhalation	Remove to fresh air, keep the patient warm and at rest. If breathing has stopped, administer artificial respiration. Give nothing by mouth. If unconscious, place in the recovery position and seek medical help.

SAFETY DATA SHEET

VINYLAST
(General colours)

Version 5.03 2005,24 March
VY/GENERAL

Page 03

5. FIRE FIGHTING MEASURES

- 5.01 Extinguishing Media Alcohol resistant foam, carbon dioxide, powder, water spray/mist.
- 5.02 Unsuitable Extinguishing Media Water jet.
- 5.03 Special Hazards Fire will produce dense black smoke containing hazardous products of combustion. (See Section 10)
- 5.04 Protective Equipment Appropriate self-contained breathing apparatus may be required.
- 5.05 Combustion Products Exposure to decomposition products may be a hazard to health.
- 5.06 Recommendations Cool closed containers exposed to fire with water spray. Do not allow run-off from fire fighting to enter drains or water courses.

6. ACCIDENTAL RELEASE MEASURES

- 6.01 Personal precautions Avoid breathing vapours. Refer to the protective measures listed in Sections 7 and 8.
- 6.02 Environmental precautions Do not allow to enter drains or water courses. If the product enters drains or sewers, the local water company should be contacted immediately; in the case of contamination of streams, rivers or lakes, the relevant environment agency.
- 6.03 Large spillages/disposal Contain and collect spillages with absorbent material which is non-combustible, e.g. sand, earth vermiculite, diatomaceous earth and place in a suitable container for disposal in accordance with the waste regulations. (See Section 13).
Clean preferably with a detergent, avoid the use of solvents.
- 6.04 General information Exclude sources of ignition and ventilate the area, also exclude non-essential personnel.

7. HANDLING & STORAGE

- 7.01 Handling Vapours are heavier than air and may spread along floors. They may form explosive mixtures with air. Prevent the creation of flammable or explosive concentrations of vapour in air and avoid vapour concentrations higher than the occupational Exposure Limit Values.
In addition, the product should only be used in areas from which all naked lights and other sources of ignition have been excluded. Electrical equipment should be protected to the appropriate standard.
The product may charge electrostatically. Always use earthing leads when transferring from one container to the other. Operators should wear anti-static footwear and clothing. Floors should be electrically conductive.
Keep container tightly closed. Exclude sources of heat, sparks and open flame. Non-sparking tools should be used.
Avoid skin and eye contact. Avoid the inhalation of vapour and mist.
Smoking, eating and drinking should be prohibited in storage and use areas.
For Occupational Exposure Control measures see

SAFETY DATA SHEET

VINYLAST
(General colours)

Version 5.03 2005,24 March
VY/GENERAL

Page 04

7. HANDLING & STORAGE (continued)

Section 8.

Never use pressure to empty: The container is not a pressure vessel. Always keep in containers made of the same material as the supply container.

The accumulation of contaminated rags may result in spontaneous combustion. Good housekeeping standards and regular safe removal of waste materials will minimise the risks of spontaneous combustion and other fire hazards.

The Manual Handling Operations Regulations may apply to the handling of containers of products. To assist in calculating the weight of the pack, the pack size in litres can be multiplied by the density given in Section 9. This will give the nett weight of the product in kilograms. Packaging allowance will be needed to estimate gross weight.

7.02 Storage

Observe the label precautions. Store between 5 C and 25 C in a dry, well ventilated place away from sources of heat, ignition and direct sunlight.

No smoking. Prevent unauthorised access.

Containers which are opened should be properly resealed and kept upright to prevent leakage.

The storage and use of this product is subject to the requirements of the Dangerous Substances and Explosive Atmospheres Regulations. Small quantities (up to 50 litres) of flammable liquids in closed containers can be kept within the work room in a suitably placed cupboard or bin which is of fire-resisting structure and is designed to retain spills. Material that is not in use should be returned to the designated storage area. Further guidance is contained in the HSE guidance note, Storage of Flammable Liquids in Containers.

The principles contained in the HSE guidance note Storage of Packed Dangerous Substances, should be observed when storing this product.

Store separately from oxidising agents and strongly alkaline and strongly acidic materials.

8. EXPOSURE CONTROLS/PERSONAL PROTECTION

8.01 Occupational exposure standards

Substance		Occupational Exposure Limits				Note
		8 Hr. TWA		15 Min. STEL		
		ppm	mg/cu. m	ppm	mg/cu. m	
XYLENE	OES	50.00	220.00	100.00	441.00	Sk
n-BUTYL ACETATE	OES	150.00	724.00	200.00	966.00	
SOLVENT NAPHTHA (PETROLEUM), LIGHT AROMATICS	OES	25.00	120.00			SUP
ETHYLBENZENE	OES	100.00	441.00	125.00	552.00	Sk
1-METHOXYPROPYL ACETATE	OES	50.00	274.00	100.00	548.00	Sk
TRIMETHYLBENZENES, all isomers/mixtures	OES	25.00	125.00			
TRIMETHYLBENZENES, all isomers/mixtures	OES	25.00	125.00			Sk

8.02 General Information

Notes:

(1) TWA is the Long Term Exposure Limit based on an 8 hour Time Weighted Average period.

SAFETY DATA SHEET

VINYLAST
(General colours)

Version 5.03 2005,24 March
VY/GENERAL

Page 05

8. EXPOSURE CONTROLS/PERSONAL PROTECTION (continued)

- (2) STEL is the Short Term Exposure Limit of 15 minutes.
- (3) "Sk" indicates a risk of exposure through the skin. "Sen" indicates a respiratory sensitiser "Carc" indicates a carcinogen.
- (4) WEL indicates a Work Exposure Limit. These are taken from EH40/2005, except those marked 'SUP' which are assigned by the supplier of the substance.

Addenda: The HSE adopted a new Work Exposure Limits (WELs) system during 2005. All of the previous MELs and some OESs have been transferred to the new system.

For sprayed products the 8 hour TWA's are:-

RESPIRABLE PARTICULATES	5 mg/cu.m (OEL)
TOTAL INHALABLE PARTICULATES	10 mg/cu.m (OEL)

ENVIRONMENTAL EXPOSURE CONTROLS:

See Section 12 for detailed information.

8.03 Engineering control measures

Provide adequate ventilation. Where reasonably practical this should be achieved by the use of local exhaust ventilation and good general extraction. If these are not sufficient to maintain concentrations of particulates and/or solvent vapours below the relevant Exposure Limit Values, suitable respiratory equipment must be worn. (See Occupational Exposure Controls below.)

OCCUPATIONAL EXPOSURE CONTROLS:

All personal protective equipment, including respiratory protective equipment, used to control exposure to hazardous substances must be selected to meet the requirements of the COSHH Regulations.

8.04 Respiratory protection

Air-fed respiratory protective equipment should be worn when this product is sprayed if the exposure of the sprayer or other people nearby can not be controlled to below the occupational exposure limit and engineering controls and methods cannot reasonably be improved.

If exposure to hazardous substances identified above cannot be controlled by the provision of local exhaust ventilation and good general extraction, suitable respiratory protective equipment should be worn. Air-fed respiratory protection should be used when painting in poorly ventilated or confined spaces.

Dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes. Wet flattening should be used wherever possible. If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory equipment should be used.

8.05 Hand protection

When skin exposure may occur, advice should be sought from glove suppliers on appropriate types and usage times for this product. The instructions and information provided by the glove supplier on use, storage and maintenance and replacement must be followed.

Barrier creams may help to protect exposed areas of the skin but are not substitutes for full

SAFETY DATA SHEET

VINYLAST
(General colours)

Version 5.03 2005,24 March
VY/GENERAL

Page 06

8. EXPOSURE CONTROLS/PERSONAL PROTECTION (continued)

- physical protection. They should not be applied once exposure has occurred.
- 8.06 Eye protection Eye protection designed to protect against liquid splashes should be worn.
- 8.07 Body protection Cotton or cotton/synthetic overalls or coveralls are normally suitable. Grossly contaminated clothing should be removed and the skin washed with soap and water or a proprietary skin cleaner. Regular skin inspection of users of this product is recommended. ALWAYS WASH YOUR HANDS BEFORE EATING, SMOKING OR USING THE TOILET.

9. PHYSICAL & CHEMICAL PROPERTIES

- 9.01 Physical State Viscous liquid
9.02 Colour Various
9.03 Odour Aromatic-ester
9.04 Boiling point/range degC 136-181
9.05 Flash point 23-31 C BS3900:A8
9.06 Lower Explosion Limit % 0.8
9.07 Solubility in water Immiscible
9.08 Vapour pressure 0.2-1.3 kPa @ 20 C
9.09 Density or relative density 1.1-1.2
9.10 Flammability Flammable
9.11 Auto-flammability 315 C
9.12 Viscosity 4-5 p @ 20 C (RT)
9.13 Vapour density (air=1) Heavier than air
9.14 General Information VOC is 570-600 gram/litre

10. STABILITY & REACTIVITY

- 10.01 Stability Stable under the recommended storage and handling conditions. (See Section 7).
- 10.02 Conditions to avoid Heat, sparks, flames and other ignition sources.
- 10.03 Materials to avoid Keep away from oxidising agents and strongly acidic and strongly alkaline materials to prevent the possibility of exothermic reaction.
- 10.04 Hazardous decomposition In a fire, hazardous decomposition products such as smoke, carbon monoxide, carbon dioxide and oxides of nitrogen may be produced.

11. TOXICOLOGICAL INFORMATION

- 11.01 Irritancy - skin XYLENE may be absorbed through the skin with possible systemic damage.
- 11.02 General Information There is no data on the product itself. The product has been assessed following the conventional method in CHIP and is classified for toxicological hazards accordingly. This takes account, where known, delayed and immediate effects and also chronic effects of components from short-term and long-term exposure by oral, inhalation and dermal routes of exposure and eye contact. See Sections 3 and 15 for details of the resulting classification.
- Exposure to organic solvent vapours in excess

SAFETY DATA SHEET

VINYLAST
(General colours)

Version 5.03 2005,24 March
VY/GENERAL

Page 07

11. TOXICOLOGICAL INFORMATION (continued)

may result in adverse health effects, such as irritation of the mucous membrane and the respiratory system and adverse effects on kidney, liver and central nervous system. Symptoms and signs include headache, dizziness, fatigue, muscular weakness, drowsiness and in extreme cases, loss of consciousness.

Solvents may cause some of the above effects by absorption through the skin. Repeated or prolonged contact with the product may cause removal of natural fats from the skin, resulting in non-allergic contact dermatitis and absorption through the skin.

Splashes in the eyes may cause irritation and reversible local damage.

12. ECOLOGICAL INFORMATION

12.01 General Information

There is no data on the product itself.

The product has been assessed following the conventional method in CHIP and is classified for ecological hazards accordingly. See Sections 3 and 15 for details.

This product should not be allowed to enter drains or water courses, or be deposited where it can affect ground or surface waters.

The Air Pollution Control requirements of the regulations made under the Environmental Protection Act may apply to the use of this product. See also Sections 5,6 and 13.

13. DISPOSAL

13.01 Product/Container Disposal

Do NOT allow into drains or water courses or dispose of where ground or surface waters may be affected.

Wastes, including empty containers, are controlled wastes and should be disposed of in accordance with the regulations made under the Control of Pollution Act and the Environmental Protection Act.

13.02 General Information

Using the information provided in this safety data sheet, advice should be obtained from the relevant environment agency whether the Special Waste Regulations apply.

14. TRANSPORT INFORMATION

14.01 General Information

VISCOUS FLAMMABLE LIQUID DEROGATION:

In pack sizes up to and including 30 litres, under the terms of 2.3.2.5, this product is not subject to the packaging, labelling and marking requirements of the IMDG Code, but both full documentation and placarding of cargo transport units is still required.

In pack sizes less than 450 litres, under the

SAFETY DATA SHEET

VINYLAST
(General colours)

Version 5.03 2005,24 March
VY/GENERAL

Page 08

14. TRANSPORT INFORMATION (continued)

terms of 2.2.3.1.5, this product is not subject to the provisions of ADR.

Air transport to be in accordance with ICAO/IATA (UN1263 PAINT Class 3 PG III)

TRANSPORT WITHIN THE USER'S PREMISES: Always transport in closed containers that are upright and secure. Ensure that persons transporting the product know what to do in the event of accident or spillage.

15. REGULATORY INFORMATION

15.01 General Information

The information contained in this safety data sheet does not constitute the users own assessment of workplace risks as required by other health and safety legislation.

The provisions of the Health and Safety at Work etc. Act and the Control of Substances Hazardous to Health Regulations apply to the use of this product at work.

The product is classified and labelled in accordance with the CHIP Regulations as follows:

15.02 EC Symbols	Flammable		Xn Harmful
15.03 R Phrases	R10	R20/21/38	R52/53
15.04 S Phrases	S07/09	S23/38	S36/37
	S43		
15.05 P Phrases	P01		

15.06 Substances which should appear on the label.

Name	Conc. Range %
XYLENE	25 - 50

15.07 R-Phrases / S-Phrases used

P01	Before use - refer to the safety data sheet.
R10	FLAMMABLE.
R20/21/38	HARMFUL BY INHALATION AND IN CONTACT WITH SKIN, ALSO IRRITATING TO THE SKIN.
R52/53	HARMFUL TO AQUATIC ORGANISMS, MAY CAUSE LONG-TERM ADVERSE EFFECTS IN THE AQUATIC ENVIRONMENT.
S07/09	Keep container tightly closed and in a well ventilated place.
S23/38	Do not breathe spray. In case of insufficient ventilation wear suitable respiratory equipment.
S36/37	Wear suitable protective clothing and gloves.
S43	In case of fire use alcohol resistant foam, carbon dioxide, powder or water spray/mist.

16. OTHER INFORMATION

16.01 Uses and Restrictions

The product should not be used for purposes other than shown in Section 1 without first referring to the supplier and obtaining written

SAFETY DATA SHEET

VINYLAST
(General colours)

Version 5.03 2005,24 March
VY/GENERAL

Page 09

16. OTHER INFORMATION (continued)

handling instructions. As the specific conditions of use of the product are outside the suppliers control, the user is responsible for ensuring that the requirements of relevant legislation are complied with.

16.02 Revisions highlighted
16.03 General Information

Section 2: Composition change.

The information contained in this safety data sheet is provided in accordance with the requirements of the CHIP Regulations.

Further information and relevant advice can be found in:

The Control of Substances Hazardous to Health Regulations 2002(SI 2002: 2677).
COSHH Essentials: easy steps to control chemicals, HSG 193. HSE books. Control Guidance Sheets, which may be relevant to the particular conditions of use, can also be found in this publication.
The Dangerous Substances & Explosive Atmospheres Regulations 2002(SI 2002: 2776).
The Manual Handling Operations Regulations 1992, (SI 1992:2793), The Stationery Office.
Chemical Warehousing: Storage of Flammable Liquids in Containers(HSG51), HSE Books.
Storage: Packaged Dangerous Substances HSG71, HSE.
The Environmental Protection (Duty of Care) Regulations 1992 (SI 1992: 2839), TSO.
A Guide to Working with Solvents (INDG 272), HSE.

16.04 Footnote

The information contained in this data sheet is based on the present state of knowledge and current national legislation. It provides guidance on health, safety and environmental aspects of the product and should not be construed as any guarantee of technical performance or suitability for particular applications.

* * * * End of Data Sheet * * * *